

Description

The 8329 *Epoxy Mold Release* is a non-silicone release agent that is formulated to prevent epoxies and other thermosetting materials from bonding to metal molds. This release agent was developed specifically for transfer and compression molding. It can be safely used on most types of plastic. It is very efficient at fully penetrating molds and forming a thin, even coat across the mold surfaces. This ensures a clean part release and glossy finish.

Benefits and Features

- **Silicone free**
- **Metal die compatible**
- **Maximum mold temperature of 260 °C [500 °F]**
- **Safe for thermosetting plastics, epoxies, nylons, and polystyrenes**

ENVIRONMENT

- ✓ RoHS
- ✓ REACH compliant

Usage Parameters

<i>Properties</i>	<i>Value</i>
Maximum Mold Temperature	260 °C [500 °F]
Shelf Life	5 y

Temperature Ranges

<i>Properties</i>	<i>Value</i>
Storage Temperature Limits ^{a)}	22 to 27 °C [72 to 80 °F]

a) Store in a dry area away from sunlight.

Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Color	Visual	Colorless
Odor		Hydrocarbon
Specific Gravity @25 °C [77 °C]	Tag closed cup	0.66 g/mL
Boiling Point		205 °C [401 °F]
Flash Point		-7 °C [19 °F]

Compatibility

Mold Release—The 8329 release agent is compatible with the following types of thermosets.

<i>Thermosetting System</i>
Epoxy Nylon Polystyrene Plastics



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Epoxy Mold Release 8329 Technical Data Sheet

8329-Aerosol

Storage

Store between 22 and 27 °C [72 and 80 °F] in dry area away from sunlight.

Health, Safety, and Environmental Awareness

Please see the 8329 **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Application Instructions

Follow the procedure below for best results.

Prerequisites

- Ensure surface to be coated is oil free, dust free and clean

To apply

1. At a distance of 20 to 25 cm (8 to 10 inches), spray a thin and even coat onto a vertical surface. For best results, use spray-and-release strokes with an even motion to avoid excess paint in one spot. Start and end each stroke off the surface.
2. If necessary, wipe off excess.

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Packaging</i>	<i>Net Weight</i>		<i>Net Volume</i>	
8329-350G	Aerosol	350 g	12.3 oz	568 mL	1.20 pt



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Epoxy Mold Release 8329 Technical Data Sheet

8329-Aerosol

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address:

Manufacturing & Support

1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office

9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.